

## Premium 85



## **Professional Grade Vinyl Electrical Tape**

## **Technical Data Sheet**

## October 2017

Description and Features	<ul> <li>Premium 85 is a 0,21 mm (8,5 mil) all weather, professional grade, pressure sensitive vinyl tape which applies easily and gives excellent performance over a wide range of temperatures. Cold and weather resistant. Flame retardant. Premium 85 can be used as primary insulation for splices up to 600 Volts. Use as protective outer jacket over splices and for all low temperature applications.</li> <li>Cold and weather resistant</li> <li>Flame retardant</li> <li>High dielectric strength</li> <li>Highly conformable</li> <li>Highly resistant to sun, water, oil, acids, alkalies, corrosive chemicals</li> <li>Meets ASTM D-3005, Type I; EN 60454-3-1, Type 11; UL 510; CSA C 22.2 no. 197; Meets 2000/53/EC and RoHS 2011/65/EU directives</li> <li>Pb, Cd, Hg, Cr (VI) free</li> </ul>				
Materials	Backing	Adhesive	Color	Standard Size	
				Width x Length	
	PVC	Rubber based	Black	19 mm x 20 m (0.75 in. x 66 ft.) Other sizes available upon request	
	Characteristic		Specification	Typical Value	Test Method
	Thickness, (mm)		0,21±0,025	0,205	ASTM D 1000
	Breaking strength (N/cm)		35 min	38	ASTM D 1000
	Elongation at break (%)		260 min	300	ASTM D 1000
	Adhesion to steel (N/cm)		1,8	2,2	ASTM D 1000
	Adhesion to backing (N/cm)		1,8	2,2	ASTM D 1000
	Flammability (seconds)		4 max.	0	ASTM D 1000
	Flagging (mm)		3 max.	ů 0	ASTM D 1000
	Temperature Rating (°C)		o max.	Ū	
	Maximum		80	80	UL510
			105	105	CSA C 22.2 no.197
	Minimum		-10	-10	UL510
			-18	-18	CSA C 22.2 no 197
	Dielectric Strength (kV)				
	-Standard		9 min	10	ASTM D 1000
	-Wet		90%	8,1	ASTM D 1000
	Dielectric Constant			3,2	ASTM D 1000
	Insulation Resistance (MΩ)			1x10 <sup>6</sup>	ASTM D 1000
Recommended Uses	Used for general splicing purposes. Can be used as primary insulation for splices up to 600 Volts Provide a protective outer jacket over splices for all low temperature applications. Can be used fo wrapping wire harnesses, and insulating degaussing coils.				
Storage	In original packaging, placed in horizontal position under cover and temperature between 5°C and 35 °C, 50-80% R.H.				
Shelf Life	60 months from date of manufacture.				

LIMITED WARRANTY: Plymouth warrants that its Product will substantially conform to that products written specifications for a period of one (1) year from the date of shipment, (Unless provided otherwise). Plymouth makes no warranty to the distributor, its customers, or the product's end user for the products merchantability and/or suitability for his/its intended use or purpose, and buyer shall assume all risks associated therewith. Provided that the product is proved to be defective within the terms described above, and provided buyer shall have first compiled with all return policies of Plymouth, PLYMOUTH'S SOLE OBLIGATION AND BUYER'S EXCLUSIVE REMEDY UNDER THIS PRODUCT WARRANTY SHALL BE TO REPLACE SUCH QUANTITY OF THE PRODUCT AS IS PROVED TO BE DEFECTIVE WITHIN THE TIME PERIOD SPECIFIED ABOVE. EXCEPT AS EXPRESSLY SET FORTH HEREIN, PLYMOUTH MAKES NO OTHER WARRANTIES, EXPRESS OR IMPLIED. In no event shall Plymouth be liable for collateral, consequential, indirect or incidental damages arising out of, or connected in any way with the supply of products. (Rev. 1/2017-2019)

Plymouth Rubber Europa, S.A. • Ctra. Porriño-Salceda, km 1,5 36400 PORRIÑO - SPAIN • Tel.: +34 986 330 562 • Fax: +34 986 336 926 www.plymouthrubber.com • info@plymouthrubber.com