# Barristo Enterprises, Inc., dba SureHold<sub>®</sub>

# SAFETY DATA SHEET

# Helios Light Cure Adhesive, Low Viscosity

# 1. IDENTIFICATION OF THE SUBSTANCE / PREPARATION AND THE COMPANY

Product Name Helios Light Cure Adhesive, Low Viscosity

Part Number 2201
Product Type Adhesive

Company Barristo Enterprises, Inc. dba SureHold

3717 N Ravenswood Avenue, Suite 243

Chicago, IL 60613 info@surehold.com www.surehold.com

Telephone + 773-472-8592; Toll Free 800-881-4495

Fax + 773-525-1750 Emergency telephone number 800-881-4495

### 2. HAZARDS IDENTIFICATION

Main hazards Warning: Combustible liquid. Causes eye irritation.

Primary Routes of Entry Skin, Eyes, Inhalation

Signs and Symptom of

Exposure

**Skin contact** – redness, inflammation

Component	NTP	ACGIH	OSHA	IARC	
No component of this product present at levels greater than or equal to 0.1% is identified as probable, possible or confirmed human carcinogen					

# 3. COMPOSITION / INFORMATION ON INGREDIENTS

Component	Conc.	CAS	ACGIH;TLV-TWA	OSHA PEL
2-Methoxyethyl Cyanoacrylate	>70- <u>&lt;</u> 98%	27816-23-5	0.2ppm TWA	None
Hydroquinone	0.01 - <0.1%	123-31-9	1 mg/m <sup>3</sup> TWA	2 mg/m <sup>3</sup> TWA

### 4. FIRST AID MEASURES

Skin contact Do not pull bonded skin apart. It may be gently peeled apart using a blunt object such as

a spoon, preferably after soaking in warm, soapy water. Cyanoacrylates give off heat on solidification. In rare cases a large drop will generate enough heat to cause a burn. Burns should be treated normally after the adhesive has been removed from the skin. If lips are accidentally stuck together, apply warm water to the lips and encourage maximum wetting and pressure from saliva inside the mouth. Peel or roll lips apart. Do

not try to pull the lips apart with direct opposing action.

Eye contact If the eye is bonded closed, release eyelashes with warm water by covering with wet

pad. Cyanoacrylate will bond to eye protein and will cause periods of weeping which will

### SUREHOLD. Helios Light Cure Adhesive, Low Viscosity, 2201

Revision 0 Revision Date 30-July-2015

help to debond the adhesive. Keep eve covered until debonding is complete, usually within 1-3 days. Do not force eye open. Medical advice should be sought in case solid particles of cyanoacrylate trapped behind the eyelid cause any abrasive damage. Ensure that breathing passages are not obstructed. The product will polymerize

immediately in the mouth making it impossible to swallow. Saliva will slowly separate the

Firefighters should wear self-contained breathing apparatus for firefighting if necessary

solidified product from the mouth (several hours).

5. FIRE FIGHTING MEASURES

Extinguishing media Use water spray, alcohol resistant foam, dry chemical or carbon dioxide.

Carbon oxides, nitrogen oxides (NOx)

Hazardous Product of

Combustion

Special Firefighting

Ingestion

**Procedures** 

Unusual Fire/Explosion Hazards

Use water spray to cool unopened containers.

Lower Explosive Limit Not determined Not determined Upper Explosive Limit

**ACCIDENTAL RELEASE MEASURES** 

Personal precautions Ensure adequate ventilation. Remove all sources of ignition. For personal protection,

see Section 8.

**Environmental precautions** Prevent further leakage or spillage if safe to do so. Do not let product enter drains or

open waters.

Cleanup methods: Do not use cloth for mopping up. Flood with water to complete polymerization and

scrape off the floor. Solid material can be disposed of as a non-hazardous waste.

7. HANDLING AND STORAGE

Handling Ventilation (low level) is recommended when using large volumes. Use of dispensing

equipment is recommended to minimize the risk of skin or eye contact. Wash hands before work breaks and after finishing work. Do not eat, drink or smoke while working.

Good industrial hygiene practices should be observed.

For optimum shelf life, store in containers under refrigerated conditions at 2-8°C (35.6 – Storage

46.4°F)

8. EXPOSURE CONTROLS / PERSONAL PROTECTION

Handle in accordance with good industrial hygiene and safety practice. Wash hands Engineering controls

before breaks and at the end of the work day.

Respiratory protection Ensure adequate ventilation.

Skin protection Handle with gloves. Gloves must be inspected prior to use. Use proper glove removal

technique (without touching gloves outer surface) to avoid skin contact with this product. Dispose of contaminated gloves after use in accordance with applicable laws and good laboratory practices. Wash and dry hands. Use impervious clothing. The type of protective equipment must be selected according to the concentration and amount of the

dangerous substance at the specific workplace.

Eye/face protection Safety glasses with side-shields conforming to EN166. Use equipment for eye protection

tested and approved under appropriate government standards such as NIOSH (US) or

EN166 (EU).

9. PHYSICAL AND CHEMICAL PROPERTIES

**Appearance** Liquid. Odor Odorless

Boiling point / range 74-76°C (165-169°F)

Flash point No data available/Not applicable рΗ No data available/Not applicable

1.06 g/cm<sup>3</sup> Density

### SUREHOLD. Helios Light Cure Adhesive, Low Viscosity, 2201

Revision 0 Revision Date 30-July-2015

Melting point / range
Solubility in Water
Viscosity
Vapor Pressure
Vapor Density (Air=1)
Evaporation Rate
No data available/Not applicable
No data available/Not applicable
No data available/Not applicable
No data available/Not applicable

# 10. STABILITY AND REACTIVITY

Reactivity No data available/Not applicable.

Stability Stable under recommended storage conditions.

Hazardous Polymerization No data available/Not applicable.
Hazardous Decomposition Products No data available/Not applicable.

Incompatible materials Reducing agents, water, amines, alcohols, alkali metals, oxidizing agents.

Conditions to Avoid Heat, flames and sparks.

Hazardous Products of Combustion No data available.

### 11. TOXICOLOGICAL INFORMATION

Acute dermal toxicity: No data available/Not applicable.

# 12. ECOLOGICAL INFORMATION

No data available

# 13. DISPOSAL CONSIDERATIONS

Recommended Method of This combustible material may be burned in a chemical incinerator equipped with an

Disposal afterburner and scrubber. Offer surplus and non-recyclable solutions to a licensed

disposal company. Contact licensed professional waste disposal service to dispose of

this material.

Disposal of uncleaned Dispose of as unused product.

packages

# 14. TRANSPORT INFORMATION

### **DOT (49CFR 172)**

### **US Department of Transportation – DOT – 49 CFR (Ground)**

Proper Shipping Name Combustible liquids, n.o.s. (Cyanoacrylate ester)

Hazard Class Combustible liquid Packaging Group III

UN/ID Number NA 1993

Exceptions (Not more than 450 liters) Unrestricted

### IATA (Air)

Proper Shipping Name Aviation regulated liquid n.o.s (Cyanoacrylate ester).

Class or Division Class 9 Packaging Group None

UN/ID Number UN 3334

Exceptions (Not more than 500 ml) Unrestricted

### IMDG (Vessel)

Proper Shipping Name Not regulated

Hazard Class None Packaging Group None UN Number None Marine pollutant None

### SUREHOLD. Helios Light Cure Adhesive, Low Viscosity, 2201

Revision 0 Revision Date 30-July-2015

# 15. REGULATORY INFORMATION

SARA Section 302 EHS None.

Sara Sections 311/312 Immediate Health Hazard, Delayed Health, Fire and Reactive.

Sara Section 313 This product contains the following toxic chemicals subject to the reporting

requirements of section 313 of the Emergency Planning and Community Right-To-

Know Act of 1986 (40 CFR 372): None.

California Proposition 65 No California Proposition 65 listed chemicals are known to be present.

TSCA 8 (b) Inventory Status All components of this product are listed (or exempt) on the EPA TSCA Inventory.

TSCA 12 (b) Export Notifications None above the reporting de Minimis.

## 16. OTHER INFORMATION

Further information

The information supplied in this Safety Data Sheet is designed only as guidance for the safe use, storage and handling of the product. This information is correct to the best of our knowledge and belief at the date of publication; however, no guarantee is made to it accuracy. This information relates only to the specific material designated and may not be valid for such material used in combination with any other materials or in any other process.